

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 254 870 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
06.11.2002 Bulletin 2002/45

(51) Int Cl.7: **C03C 17/245, C03C 17/34,
C23C 16/40**

(21) Application number: **02009640.0**

(22) Date of filing: **01.06.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **Ammerlaan, Johannes Andreas Maria**
5615 CJ Eindhoven (NL)
• **McCurdy, Richard Joseph**
Aurora, IL 60506 (US)
• **Hurst, Simon James**
Cheshire WA7 1QW (GB)

(30) Priority: **08.06.1999 GB 9913315**

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
00935378.0 / 1 198 431

(74) Representative: **Halliwell, Anthony Charles et al**
Group Intellectual Property Dept,
Pilkington European Technical Centre,
Pilkington plc,
Hall Lane,
Lathom
Ormskirk, Lancashire L40 5UF (GB)


(71) Applicants:
• **PILKINGTON PLC**
St. Helens, Merseyside WA10 3TT (GB)
• **Pilkington North America, Inc.,**
as Libbey-Owens-Ford Co
Toledo, Ohio 43695 (US)

Remarks:
This application was filed on 27 - 04 - 2002 as a
divisional application to the application mentioned
under INID code 62.

(54) **Photocatalytically active coated substrates**

(57) A self cleaning photocatalytically active coated substrate, especially a glass substrate, is disclosed, the coated substrate having a photocatalytically active titanium oxide coating on one surface thereof. The coated substrate exhibits, in one aspect, high photocatalytic ac-

tivity of greater than $5 \times 10^{-3} \text{ cm}^{-1} \text{ min}^{-1}$ and low visible light reflection measured on the coated side of 35% or lower and in another aspect is durable to abrasion such that the coated surface remains photocatalytically active after it has been subjected to 300 strokes of the European standard abrasion test.



EP 1 254 870 A2

Description

[0001] This invention relates to photocatalytically active coated substrates, in particular, but not exclusively, it relates to photocatalytically active coated glass.

5 [0002] It is known to deposit thin coatings having one or more layers, with a variety of properties, on to substrates including on to glass substrates. One property of interest is photocatalytic activity which arises by the photogeneration, in a semiconductor, of a hole-electron pair when the semiconductor is illuminated by light of a particular frequency. The hole-electron pair can be generated in sunlight and can react in humid air to form hydroxy and peroxy radicals on the surface of the semiconductor. The radicals oxidise organic grime on the surface. This property has an application
10 in self-cleaning substrates, especially in self-cleaning glass for windows.

[0003] Titanium dioxide may be an efficient photocatalyst and may be deposited on to substrates to form a transparent coating with photocatalytic self-cleaning properties. Titanium oxide photocatalytic coatings are disclosed in EP 0 901 991 A2, WO 97/07069, WO 97/10186, WO 98/41480, in Abstract 735 of 187th Electrochemical Society Meeting (Reno, NV, 95-1, p.1102) and in New Scientist magazine (26 August 1995, p.19). In WO 98/06675 a chemical vapour deposition
15 process is described for depositing titanium oxide coatings on hot flat glass at high deposition rate using a precursor gas mixture of titanium chloride and an organic compound as source of oxygen for formation of the titanium oxide coating.

[0004] It has been thought that relatively thick titanium oxide coatings need to be deposited to provide good photocatalytic activity. For example, in WO 98/41480 it is stated that a photocatalytically active self-cleaning coating must
20 be sufficiently thick so as to provide an acceptable level of activity and it is preferred that such a coating is at least about 200Å and more preferably at least about 500Å thick (the measured thickness of the titanium oxide coatings produced in the Examples all being in the range 400Å to 2100Å).

[0005] However, a problem of relatively thick titanium oxide coatings is high visible light reflection and thus relatively low visible light transmission. This problem is recognised in the article in New Scientist magazine in relation to coated
25 windcreens, where it is suggested that to reduce the effect of high reflection, dashboards might have to be coated in black velvet or some other material that does not reflect light into a coated windscreen.

[0006] EP 0 901 991A2 referred to above, relates to photocatalytic glass panes with a coating of titanium oxide of a particular crystal structure characterised by the presence of particular peaks in its X-ray diffraction pattern. The specification contemplates a range of coating thickness (with the specific Examples all having thickness in the range 20
30 nm to 135 nm, the thinner coatings being less photocatalytically active than the thicker coatings). The specification also contemplates a range of deposition temperatures from as low as 300°C to as high as 750°C, but prefers temperatures in the range 400°C to 600°C, and in all the specific Examples of the invention the titanium dioxide layer is deposited at a temperature in or below this preferred range.

[0007] The applicants have now found that by depositing the titanium oxide coatings at higher temperatures, especially temperatures above 600°C, they are able to achieve coatings with an enhanced photocatalytic activity for a given thickness, enabling the same photocatalytic performance to be achieved with thinner coatings. Such thinner coatings
35 tend to have, advantageously, lower visible light reflection and, apparently in consequence of their higher deposition temperature, improved durability, especially to abrasion and temperature cycling in a humid atmosphere.

[0008] The present invention accordingly provides a process for the production of a photocatalytically active coated substrate which comprises depositing a titanium oxide coating on the surface of a substrate by contacting the surface
40 of the substrate with a fluid mixture containing a source of titanium and a source of oxygen, said substrate being at a temperature of at least 600°C, whereby the coated surface of the substrate has a photocatalytic activity of greater than $5 \times 10^{-3} \text{ cm}^{-1} \text{ min}^{-1}$ and a visible light reflection measured on the coated side of 35% or lower.

[0009] Preferably, the substrate is at a temperature in the range 625°C to 720°C, more preferably the substrate is
45 at a temperature in the range 645°C to 720°C.

[0010] Advantageously, the fluid mixture comprises titanium chloride as the source of titanium and an ester other than a methyl ester. Thus, in a preferred embodiment, the present invention provides a process for the production of a photocatalytically active coated substrate which comprises depositing a titanium oxide coating having a thickness of
50 less than 40 nm on a substrate by contacting a surface of the substrate with a fluid mixture comprising titanium chloride and an ester other than a methyl ester.

[0011] The process may be performed wherein the surface of the substrate is contacted with the fluid mixture when the substrate is at a temperature in the range 600°C to 750°C.

[0012] Preferably, the ester is an alkyl ester having an alkyl group with a β hydrogen (the alkyl group of an alkyl ester is the group derived from the alcohol in synthesis of an ester and a β hydrogen is a hydrogen bonded to a carbon atom
55 β to the oxygen of the ether linkage in an ester). Preferably the ester is a carboxylate ester.

[0013] Suitable esters may be alkyl esters having a C_2 to C_{10} alkyl group, but preferably the ester is an alkyl ester having a C_2 to C_4 alkyl group.

[0014] Preferably, the ester is a compound of formula:

$R - C(O) - O - C(X)(X') - C(Y)(Y') - R'$, where R and R' represent hydrogen or an alkyl group, X, X', Y and Y' represent monovalent substituents, preferably alkyl groups or hydrogen atoms and wherein at least one of Y and Y' represents hydrogen.

[0015] Suitable esters that may be used in the process of the present invention include: ethyl formate, ethyl acetate, ethyl propionate, ethyl butyrate, n-propyl formate, n-propyl acetate, n-propyl propionate, n-propyl butyrate, isopropyl formate, isopropyl acetate, isopropyl propionate, isopropyl butyrate, n-butyl formate, n-butyl acetate and t-butyl acetate.

[0016] Preferably, the ester comprises an ethyl ester, more preferably the ester comprises ethyl formate, ethyl acetate or ethyl propionate. Most preferably the ester comprises ethyl acetate.

[0017] The fluid mixture may be in the form of a liquid, especially dispersed as a fine spray (a process often referred to as spray deposition), but preferably the fluid mixture is a gaseous mixture. A deposition process performed using a gaseous mixture as precursor is often referred to as chemical vapour deposition (CVD). The preferred form of CVD is laminar flow CVD, although turbulent flow CVD may also be used.

[0018] The process may be performed on substrates of various dimensions including on sheet substrates, especially on cut sheets of glass, or preferably on-line during the float glass production process on a continuous ribbon of glass.

Thus, preferably, the process is performed on-line during the float glass production process and the substrate is a glass ribbon. If the process is performed on line, it is preferably performed on the glass ribbon whilst it is in the float bath.

[0019] An advantage of performing the process on-line is that coatings deposited on-line tend to be durable and in particular to have good abrasion and chemical resistance.

[0020] An on-line deposition process is preferably, and other deposition processes may be, performed at substantially atmospheric pressure.

[0021] In a particularly preferred embodiment there is provided a process for the production of a durable photocatalytically active coated glass which comprises depositing on the surface of a glass substrate a photocatalytically active titanium oxide layer by contacting the surface of the substrate, which is at a temperature in the range 645°C to 720°C, preferably in the range 670°C to 720°C with a fluid mixture containing a source of titanium.

[0022] As noted above, the applicants have found that by depositing the titanium oxide at high temperature, a coating of relatively high photocatalytic activity for its thickness may be produced and, as coatings of reduced thickness tend to have lower reflection, the invention also provides novel products having an advantageous combination of high photocatalytic activity with moderate or low light reflection.

[0023] Thus, the present invention, in another aspect, provides a photocatalytically active coated substrate comprising a substrate having a photocatalytically active titanium oxide coating on one surface thereof, characterised in that the coated surface of the substrate has a photocatalytic activity of greater than $5 \times 10^{-3} \text{ cm}^{-1} \text{ min}^{-1}$ and in that the coated substrate has a visible light reflection measured on the coated side of 35% or lower.

[0024] High photocatalytic activity is advantageous because the amount of contaminants (including dirt) on the coated surface of the photocatalytically active coated substrate will be reduced quicker than on substrates with relatively low photocatalytic activity. Also, relatively quick removal of surface contaminants will tend to occur at low levels of UV light intensity.

[0025] Photocatalytic activity for the purposes of this specification is determined by measuring the rate of decrease of the integrated absorbance of the infra-red absorption peaks corresponding to the C-H stretches of a thin film of stearic acid, formed on the coated substrate, under illumination by UV light from a UVA lamp having an intensity of about 32 W/m^2 at the surface of the coated substrate and a peak wavelength of 351 nm. The stearic acid may be formed on the coated substrate by spin casting a solution of stearic acid in methanol as described below.

[0026] Preferably, the coated surface of the substrate has a photocatalytic activity of greater than $1 \times 10^{-2} \text{ cm}^{-1} \text{ min}^{-1}$, more preferably of greater than $3 \times 10^{-2} \text{ cm}^{-1} \text{ min}^{-1}$.

[0027] Low visible light reflection is advantageous because it is less distracting than high reflection and, especially for glass substrates, low visible light reflection corresponds to high visible transmission which is often required in architectural and especially automotive applications of glass.

[0028] Preferably, the coated substrate has a visible reflection measured on the coated side of 20% or lower more preferably of 17% or lower and most preferably of 15% or lower.

[0029] In most embodiments of the invention the substrate will be substantially transparent and in a preferred embodiment of the invention the substrate comprises a glass substrate. Usually the glass substrate will be a soda lime glass substrate.

[0030] Where the substrate is a soda lime glass substrate or other alkali metal ion containing substrate, the coated substrate preferably has an alkali metal ion blocking underlayer between the surface of the substrate and the photocatalytically active titanium oxide coating. This reduces the tendency for alkali metal ions from the substrate to migrate into the photocatalytically active titanium oxide coating which is advantageous because of the well known tendency of alkali metal ions to poison semiconductor oxide coatings, reducing their activity.

[0031] The alkali metal ion blocking underlayer may comprise a metal oxide but preferably the alkali metal ion blocking layer is a layer of silicon oxide. The silicon oxide may be silica but will not necessarily be stoichiometric and may

comprise impurities such as carbon (often referred to as silicon oxycarbide and deposited as described in GB 2,199,848B) or nitrogen (often referred to as silicon oxynitride).

[0032] It is advantageous if the alkali metal ion blocking underlayer is thin so that it has no significant effect on the optical properties of the coating, especially by reducing the transparency of a transparent coated substrate or causing interference colours in reflection or transmission. The suitable thickness range will depend on the properties of the material used to form the alkali metal ion blocking layer (especially its refractive index), but usually the alkali metal ion blocking underlayer has a thickness of less than 60 nm and preferably has a thickness of less than 40 nm. Where present, the alkali metal ion blocking underlayer should always be thick enough to reduce or block migration of alkali metal ions from the glass into the titanium oxide coating.

[0033] An advantage of the present invention is that the photocatalytically active titanium oxide coating is thin (contributing to the low visible reflection of the coated substrate) but the coated substrate still has excellent photocatalytic activity. Preferably, the titanium oxide coating has a thickness of 30 nm or lower, more preferably the titanium oxide coating has a thickness of 20 nm or lower and most preferably the titanium oxide coating has a thickness in the range 2 nm to about 20 nm.

[0034] The present invention is also advantageous because depositing thin titanium oxide coatings requires less precursor and the layers can be deposited in a relatively short time. A thin titanium oxide coating is also less likely to cause interference colours in reflection or transmission. However, a particular advantage is that the visible light reflection of a thin titanium oxide coating is low which is especially important when the coated substrate is coated glass. Usually the required visible light transmission of the coated glass will determine the thickness of the titanium oxide coating.

[0035] Preferably, the coated surface of the substrate has a static water contact angle of 20° or lower. Freshly prepared or cleaned glass has a hydrophilic surface (a static water contact angle of lower than about 40° indicates a hydrophilic surface), but organic contaminants rapidly adhere to the surface increasing the contact angle. A particular benefit of coated substrates (and especially coated glasses) of the present invention is that even if the coated surface is soiled, irradiation of the coated surface by UV light of the right wavelength will reduce the contact angle by reducing or destroying those contaminants. A further advantage is that water will spread out over the low contact angle surface reducing the distracting effect of droplets of water on the surface (e.g. from rain) and tending to wash away any grime or other contaminants that have not been destroyed by the photocatalytic activity of the surface. The static water contact angle is the angle subtended by the meniscus of a water droplet on a glass surface and may be determined in a known manner by measuring the diameter of a water droplet of known volume on a glass surface and calculated using an iterative procedure.

[0036] Preferably, the coated substrate has a haze of 1% or lower, which is beneficial because this allows clarity of view through a transparent coated substrate.

[0037] In preferred embodiments, the coated surface of the substrate is durable to abrasion, such that the coated surface remains photocatalytically active after it has been subjected to 300 strokes of the European standard abrasion test. Preferably, the coated surface remains photocatalytically active after it has been subjected to 500 strokes of the European standard abrasion test, and more preferably the coated surface remains photocatalytically active after it has been subjected to 1000 strokes of the European standard abrasion test.

[0038] This is advantageous because self-cleaning coated substrates of the present invention will often be used with the coated surface exposed to the outside (e.g. coated glasses with the coated surface of the glass as the outer surface of a window) where the coating is vulnerable to abrasion.

[0039] The European standard abrasion test refers to the abrasion test described in European standard BS EN 1096 Part 2 (1999) and comprises the reciprocation of a felt pad at a set speed and pressure over the surface of the sample.

[0040] In the present specification, a coated substrate is considered to remain photocatalytically active if, after being subjected to the European abrasion test, irradiation by UV light (e.g. of peak wavelength 351 nm) reduces the static water contact angle to below 15°. To achieve this contact angle after abrasion of the coated substrate will usually take less than 48 hours of irradiation at an intensity of about 32 W/m² at the surface of the coated substrate.

[0041] Preferably, the haze of the coated substrate is 2% or lower after being subjected to the European standard abrasion test.

[0042] Durable coated substrates according to the present invention may also be durable to humidity cycling (which is intended to have a similar effect to weathering). Thus, in preferred embodiments of the invention, the coated surface of the substrate is durable to humidity cycling such that the coated surface remains photocatalytically active after the coated substrate has been subjected to 200 cycles of the humidity cycling test. In the present specification, the humidity cycling test refers to a test wherein the coating is subjected to a temperature cycle of 35°C to 75°C to 35°C in 4 hours at near 100% relative humidity. The coated substrate is considered to remain photocatalytically active, if, after the test, irradiation by UV light reduces the static water contact angle to below 15°.

[0043] In a further preferred embodiment, the present invention provides a durable photocatalytically active coated glass comprising a glass substrate having a coating on one surface thereof, said coating comprising an alkali metal

ion blocking underlayer and a photocatalytically active titanium oxide layer, wherein the coated surface of the substrate is durable to abrasion such that the coated surface remains photocatalytically active after it has been subjected to 300 strokes of the European standard abrasion test. In this embodiment, the coated glass preferably has a visible light reflection measured on the coated side of 35% or lower, and the photocatalytically active titanium oxide layer preferably has a thickness of 30 nm or lower. Thin coatings are durable to abrasion which is surprising because previously it has been thought that only relatively thick coatings would have good durability.

[0044] In a still further embodiment, the present invention provides a coated glass comprising a glass substrate having a photocatalytically active titanium oxide coating on one surface thereof, characterised in that the coated surface of the glass has a photocatalytic activity of greater than $4 \times 10^{-2} \text{cm}^{-1} \text{min}^{-1}$, preferably greater than $6 \times 10^{-2} \text{cm}^{-1} \text{min}^{-1}$ and more preferably greater than $8 \times 10^{-2} \text{cm}^{-1} \text{min}^{-1}$ and in that the coated glass has a visible light reflection measured on the coated side of less than 20%.

[0045] Coated substrates according to the present invention have uses in many areas, for example as glazings in windows including in a multiple glazing unit comprising a first glazing pane of a coated substrate in spaced opposed relationship to a second glazing pane, or, when the coated substrate is coated glass, as laminated glass comprising a first glass ply of the coated glass, a polymer interlayer (of, for example, polyvinylbutyral) and a second glass ply.

[0046] In addition to uses in self-cleaning substrates (especially self-cleaning glass for windows), coated substrates of the present invention may also be useful in reducing the concentration of atmospheric contaminants. For example, coated glass under irradiation by light of UV wavelengths (including UV wavelengths present in sunlight) may destroy atmospheric contaminants for example, nitrogen oxides, ozone and organic pollutants, adsorbed on the coated surface of the glass. This use is particularly advantageous in the open in built-up areas (for example, in city streets) where the concentration of organic contaminants may be relatively high (especially in intense sunlight), but where the available surface area of glass is also relatively high. Alternatively, the coated glass (with the coated surface on the inside) may be used to reduce the concentration of atmospheric contaminants inside buildings, especially in office buildings having a relatively high concentration of atmospheric contaminants.

[0047] The invention is illustrated but not limited by the following drawings.

[0048] Figure 1 is a graph of photocatalytic activity of coated glass produced by a process according to the invention as a function of the thickness of the titanium oxide layer.

[0049] Figure 2 illustrates apparatus for on line chemical vapour deposition of coatings according to the invention.

[0050] In Figure 1 the coated glasses were produced using an on-line CVD process as described in the Examples, below. The open circles 1 relate to titanium oxide layers deposited using titanium tetrachloride as titanium precursor, and the crosses 2 relate to titanium oxide layers deposited using titanium tetraethoxide as titanium precursor.

[0051] The layers of the coating may be applied on line onto the glass substrate by chemical vapour deposition during the glass manufacturing process. FIG. 2 illustrates an apparatus, indicated generally at 10, useful for the on line production of the coated glass article of the present invention, comprising a float section 11, a Lehr 12, and a cooling section 13. The float section 11 has a bottom 14 which contains a molten tin bath 15, a roof 16, sidewalls (not shown), and end walls 17, which together form a seal such that there is provided an enclosed zone 18, wherein a non-oxidising atmosphere is maintained to prevent oxidation of the tin bath 15. During operation of the apparatus 10, molten glass 19 is cast onto a hearth 20, and flows therefrom under a metering wall 21, then downwardly onto the surface of the tin bath 15, forming a float glass ribbon 37, which is removed by lift-out rolls 22 and conveyed through the Lehr 12, and thereafter through the cooling section 13.

[0052] A non-oxidising atmosphere is maintained in the float section 11 by introducing a suitable gas, such as for example one comprising nitrogen and 2% by volume hydrogen, into the zone 18, through conduits 23 which are operably connected to a manifold 24. The non-oxidizing gas is introduced into the zone 18 from the conduits 23 at a rate sufficient to compensate for losses of the gas (some of the non-oxidizing atmosphere leaves the zone 18 by flowing under the end walls 17), and to maintain a slight positive pressure above ambient pressure. The tin bath 15 and the enclosed zone 18 are heated by radiant heat directed downwardly from heaters 25. The heat zone 18 is generally maintained at a temperature of about 1330°F to 1400°F (721°C to 760°C). The atmosphere in the Lehr 12 is typically air, and the cooling section 13 is not enclosed. Ambient air is blown onto the glass by fans 26.

[0053] The apparatus 10 also includes coaters 27, 28, 29 and 30 located in series in the float zone 11 above the float glass ribbon 37. The precursor gaseous mixtures for the individual layers of the coating are supplied to the respective coaters, which in turn direct the precursor gaseous mixtures to the hot surface of the float glass ribbon 37. The temperature of the float glass ribbon 37 is highest at the location of the coater 27 nearest the hearth 20 and lowest at the location of the coater 30 nearest the Lehr 12.

[0054] The invention is further illustrated by the following Examples, in which coatings were applied by laminar flow chemical vapour deposition in the float bath on to a moving ribbon of float glass during the glass production process. In the Examples two layer coatings were applied to the glass ribbon.

[0055] All gas volumes are measured at standard temperature and pressure unless otherwise stated. The thickness values quoted for the layers were determined using high resolution scanning electron microscopy and optical modelling

of the reflection and transmission spectra of the coated glass. Thickness of the coatings was measured with an uncertainty of about 5%. The transmission and reflection properties of the coated glasses were determined using an Hitachi U - 4000 spectrophotometer. The a, b and L* values mentioned herein of the transmission and/or reflection colour of the glasses refer to the CIE Lab colours. The visible reflection and visible transmission of the coated glasses were determined using the D65 illuminant and the standard CIE 2° observer in accordance with the ISO 9050 standard (Parry Moon airmass 2) The haze of the coated glasses was measured using a WYK - Gardner Hazeguard+ haze meter.

[0056] The photocatalytic activity of the coated glasses was determined from the rate of decrease of the area of the infrared peaks corresponding to C-H stretches of a stearic acid film on the coated surface of the glass under illumination by UVA light. The stearic acid film was formed on samples of the glasses, 7-8 cm square, by spin casting 20 µl of a solution of stearic acid in methanol (8.8×10^{-3} mol dm⁻³) on the coated surface of the glass at 2000 rpm for 1 minute. Infra red spectra were measured in transmission, and the peak height of the peak corresponding to the C-H stretches (at about 2700 to 3000 cm⁻¹) of the stearic acid film was measured and the corresponding peak area determined from a calibration curve of peak area against peak height. The coated side of the glass was illuminated with a UVA-351 lamp (obtained from the Q-Panel Co., Cleveland, Ohio, USA) having a peak wavelength of 351 nm and an intensity at the surface of the coated glass of approximately 32 W / m². The photocatalytic activity is expressed in this specification either as the rate of decrease of the area of the IR peaks (in units of cm⁻¹ min⁻¹) or as t_{90%} (in units of min) which is the time of UV exposure taken to reduce the peak height (absorption) of a peak in the wavelength area down to 10% of its initial value.

[0057] The static water contact angle of the coated glasses was determined by measuring the diameter of a water droplet (volume in the range 1 to 5 µl) placed on the surface of the coated glass after irradiation of the coated glass using the UVA 351 lamp for about 2 hours (or as otherwise specified).

Examples 1-15

[0058] A ribbon of 1 mm thick soda lime float glass advancing at a lehr speed of 300 m/hour was coated with a two-layer coating as the ribbon advanced over the float bath at a position where the glass temperature was in the range of about 650°C to about 670°C. The float bath atmosphere comprised a flowing gaseous mixture of nitrogen and 9% hydrogen at a bath pressure of approximately 0.15 mbar.

[0059] Layer 1 (the first layer to be deposited on the glass) was a layer of silicon oxide. Layer 1 was deposited by causing a gaseous mixture of monosilane (SiH₄, 60 ml/min), oxygen (120 ml/min), ethylene (360 ml/min) and nitrogen (8 litres/min) to contact and flow parallel to the glass surface in the direction of movement of the glass using coating apparatus as described in GB patent specification 1 507 966 (referring in particular to Fig. 2 and the corresponding description on page 3 line 73 to page 4 line 75) with a path of travel of the gaseous mixture over the glass surface of approximately 0.15 m. Extraction was at approximately 0.9 to 1.2 mbar. The glass ribbon was coated across a width of approximately 10 cm at a point where its temperature was approximately 670°C. The thickness of the silica layer was about 20 to 25 nm.

[0060] Layer 2 (the second layer to be deposited) was a layer of titanium dioxide. Layer 2 was deposited by combining separate gas streams comprising titanium tetrachloride in flowing nitrogen carrier gas, ethyl acetate in flowing nitrogen carrier gas and a bulk flow of nitrogen of 8 l/min (flow rate measured at 20 psi) into a gaseous mixture and then delivering (through lines maintained at about 250°C) the gaseous mixture to coating apparatus consisting of an oil cooled dual flow coater. The pressure of the nitrogen carrier and bulk nitrogen gases was approximately 20 pounds per square inch. The gaseous mixture contacted and flowed parallel to the glass surface both upstream and downstream along the glass ribbon. The path of travel of the gaseous mixture downstream was about 0.15 m and upstream was about 0.15 m with extraction of about 0.15 mbar. Titanium tetrachloride and ethyl acetate were entrained in separate streams of flowing nitrogen carrier gas by passing nitrogen through bubblers containing either titanium tetrachloride or ethyl acetate. The flow rates of the nitrogen carrier gases are described in Table 1 (the flow rates were measured at 20 psi). The titanium tetrachloride bubbler was maintained at a temperature of 69°C and the ethyl acetate bubbler was maintained at a temperature of 42°C. The estimated flow rates of entrained titanium tetrachloride and entrained ethyl acetate are also described in Table 1 for each of the Examples 1 to 15.

[0061] The properties of the two-layer coatings were measured. Values of the thickness of layer 2 (the titanium oxide layer), and values of the visible reflection measured on the coated side, L* and haze of the coated glasses are described in Table 2 for the Examples 1-15. The haze of each coated glass was below 0.2 %.

[0062] The photocatalytic activity and static water contact angle of the coated glasses were determined. The initial peak height and initial peak area of the IR peaks corresponding to the stearic acid C-H stretches, the photocatalytic activity, the static water contact angle and t_{90%} for the Examples 1-15 are described in Table 3. The thickness of the titanium oxide layer, surprisingly has little effect on photocatalytic activity.

Examples 16-19

[0063] Examples 16-19 were conducted under the same conditions as Examples 1-15 except that the bath pressure was approximately 0.11 mbar, extraction for deposition of the silica undercoat (layer 1) was approximately 0.7 mbar, the titanium tetrachloride bubbler was maintained at a temperature of approximately 100°C, the ethyl acetate bubbler was maintained at a temperature of approximately 45°C and the delivery lines were maintained at a temperature of approximately 220°C.

[0064] The flow rates of nitrogen carrier gas, and the estimated flow rates of entrained titanium tetrachloride and entrained ethyl acetate are disclosed for each of the examples 16-19 in Table 1.

[0065] Values of the estimated thickness of layer 2 (the titanium oxide layer), and values of visible reflection measured on the coated side, L* and haze of the coated glasses are described in Table 2 for each of the Examples 16-19.

[0066] The initial peak height and initial peak area of the IR peaks corresponding to the stearic acid C-H stretches, the photocatalytic activity, $t_{90\%}$ and the static water contact angle and for each of the Examples 16-19 are described in Table 3.

[0067] The photocatalytic activity of the Examples 16-19 was not substantially greater than that of the Examples 1-15 despite the thicker titanium oxide (and hence more reflective) coatings.

TABLE 1

Example	Nitrogen Carrier Gas Flow Rates to Bubblers (l / min, measured at 20 psi)		TiCl ₄ flow rate (l / min)	Ethyl Acetate flow rate (l / min)
	TiCl ₄ Bubbler	Ethyl Acetate Bubbler		
1	0.16	1	0.032	0.46
2	0.12	0.3	0.024	0.14
3	0.12	0.45	0.024	0.21
4	0.08	0.2	0.016	0.09
5	0.12	0.15	0.024	0.07
6	0.12	0.75	0.024	0.35
7	0.08	0.3	0.016	0.14
8	0.08	0.5	0.016	0.23
9	0.04	0.1	0.008	0.05
10	0.04	0.15	0.008	0.07
11	0.04	0.25	0.008	0.12
12	0.16	0.1	0.032	0.05
13	0.08	0.1	0.016	0.05
14	0.16	0.4	0.032	0.19
15	0.16	0.2	0.032	0.09
16	0.1	0.5	0.088	0.27
17	0.08	0.4	0.070	0.22
18	0.06	0.3	0.053	0.16
19	0.04	0.2	0.035	0.11

TABLE 2

Example	Thickness of titanium oxide layer (nm)	Visible reflection of coated glass (%)	L* value of coated glass (%)	Haze (%)
1	15	14.1	44	0.12
2	14.3	13.9	44	0.07

TABLE 2 (continued)

Example	Thickness of titanium oxide layer (nm)	Visible reflection of coated glass (%)	L* value of coated glass (%)	Haze (%)
3	14.2	13.2	43	0.12
4	11.3	11.4	40	0.08
5	12.1	12.1	41	0.08
6	11.0	a	a	0.07
7	8	a	a	0.11
8	7.2	9.7	37	0.04
9	6.1	9.1	36	0.05
10	5.6	9	36	0.07
11	4.6	8.7	35	0.06
12	15.6	15.4	46	0.1
13	16.0	a	a	0.13
14	17.5	16.2	47	0.14
15	20.3	19.5	51	0.1
16	a	28.4	47.8	0.3
17	ca 68	29.1	58.4	0.37
18	ca 32	25.9	55.6	0.24
19	ca 27	20.5	50.2	0.2

a Not measured

TABLE 3

Example	IR Peaks corresponding to stearic acid film C-H stretches (2700 - 3000 cm ⁻¹)		Photocatalytic Activity (x 10 ⁻² cm ⁻¹ min ⁻¹)	Static Water Contact Angle (°)	t _{90%} (min)
	Initial Peak Height (arbitrary units)	Initial Peak Area (cm ⁻¹)			
1	0.030	1.04	9.4	17 ± 5	10
2	0.0331	1.15	10.4	15 ± 1	10
3	0.0311	1.08	12.2	13 ± 2	8
4	0.0324	1.13	6.8	14 ± 1	15
5	0.0287	1.00	8.2	16 ± 3	11
6	0.028	0.98	8.8	15 ± 1	10
7	0.0343	1.20	10.8	15 ± 1	10
8	0.0289	1.03	6.6	16 ± 1	14
9	0.0289	1.01	6.5	14 ± 2	14
10	0.0278	0.97	6.2	18 ± 2	14
11	0.0344	1.20	5.4	18 ± 1	20
12	0.0291	1.02	10.2	12 ± 1	9
13	0.0289	1.01	9.1	14 ± 2	10

TABLE 3 (continued)

Example	IR Peaks corresponding to stearic acid film C-H stretches (2700 - 3000 cm^{-1})		Photocatalytic Activity ($\times 10^{-2} \text{ cm}^{-1} \text{ min}^{-1}$)	Static Water Contact Angle ($^{\circ}$)	$t_{90\%}$ (min)
	Initial Peak Height (arbitrary units)	Initial Peak Area (cm^{-1})			
14	0.0269	0.94	9.4	15 ± 2	9
15	0.0331	1.15	8.7	15 ± 2	12
16	0.0227	0.79	17.8	12	4
17	0.026	0.91	10.2	12	8
18	0.0225	0.79	10.1	13	7
19	0.0258	0.90	10.1	16	8

Examples 20-27

[0068] The Examples 20-27 were conducted under the same conditions as Examples 1-15 except that layer 2 was deposited from a gaseous mixture comprising titanium tetraethoxide entrained in nitrogen carrier gas by passing the carrier gas through a bubbler containing titanium tetraethoxide maintained at a temperature of 170°C. The flow rates of nitrogen carrier gas (measured at 20 psi) and titanium tetraethoxide are described in Table 4 for each of the Examples 20-27. The flow rate of bulk nitrogen gas was 8.5 l/min (measured at 20 psi).

[0069] The properties of the two-layer coatings were measured. Values of the thickness of layer 2 (the titanium oxide layer), and values of the visible reflection measured on the coated side and haze of the coated glasses are described in Table 5 for the Examples 20-27. The haze of each coated glass was below 0.7%.

[0070] The photocatalytic activity and static water contact angle of the coated glasses were determined. The initial peak height and initial peak area of the IR peaks corresponding to the stearic acid C-H stretches, the photocatalytic activity and $t_{90\%}$, and the static water contact angle for each of the Examples 20-27 are described in Table 6.

Examples 28 and 29

[0071] The Examples 28 and 29 were conducted under the same conditions as Examples 20-27 except that the titanium tetraethoxide bubbler was maintained at a temperature of 168°C and the bath pressure was 0.11 mbar. Data relating to Examples 28-29 equivalent to data for Examples 20-27 are described in Tables 4, 5 and 6.

TABLE 4

Example	Nitrogen Carrier Gas Flow Rates to Titanium tetraethoxide bubbler (l / min, measured at 20 psi)	Titanium ethoxide flow rate (l / min)
20	0.25	0.014
21	0.15	0.008
22	0.2	0.011
23	0.25	0.014
24	0.3	0.017
25	0.35	0.019
26	0.2	0.011
27	0.1	0.006
28	0.6	0.030
29	0.4	0.020

TABLE 5

Example	Thickness of titanium oxide layer (nm)	Visible reflection of coated glass (%)	Haze (%)
20	13	a	0.4
21	13	a	0.29
22	16	15.7	0.29
23	18	a	0.28
24	24	a	a
25	26	a	0.61
26	9.9	10.9	0.19
27	4.7	8.8	0.29
28	38.3	35.2	0.29
29	31.9	28.4	0.22

a Not measured

TABLE 6

Example	IR Peaks corresponding to stearic acid film C-H stretches (2700 - 3000 cm ⁻¹)		Photocatalytic Activity (x 10 ⁻² cm ⁻¹ min ⁻¹)	Static Water Contact Angle (°)	t _{90%} (min)
	Initial Peak Height (arbitrary units)	Initial Peak Area (cm ⁻¹)			
20	0.027	0.953	5.7	19±5	15
21	0.031	1.095	5.7	a	17
22	0.024	0.838	3.6	15±2	21
23	0.030	1.029	7.1	11±3	13
24	0.029	1.015	7	17±3	13
25	0.031	1.071	7.4	13±4	13
26	0.031	1.085	4.4	21±3	22
27	0.029	0.998	3.2	16±5	28
28	0.021	0.733	3.6	13	18
29	0.024	0.848	3.3	14	23

a Not measured

Examples 30-42

[0072] In Examples 30 to 42, two-layer coatings were applied by on line CVD to a float glass ribbon across its full width of approximately 132 inches (3.35m) in the float bath during the float glass production process. The apparatus used to deposit the coating is illustrated in Figure 2. The float bath atmosphere comprised nitrogen and 2% by volume hydrogen. Bath pressure was 0.15 mbar.

[0073] The two layer coating consisted of a silicon oxide layer deposited first on the float glass ribbon and titanium oxide layer deposited on to the silicon oxide layer. The precursor chemistry of the gaseous mixtures used to deposit the coating was the same as that used in Examples 1-15. The temperature of deposition of the layers was varied by using different coaters 27, 28, 29 or 30 (referring to Figure 2). Coater 27 located nearest the hearth being hottest and coater 30 located nearest the lehr being coolest. In Examples 30-33 and 42 two coaters (28 and 29 in Examples 30-33 and coaters 27 and 28 in Example 42) were used to deposit the silicon oxide coating. The benefit of using two coaters to deposit the silicon oxide layer is that longer production run times are possible.

[0074] The gaseous mixture used to deposit the silicon oxide layer for Examples 30 to 41 consisted of the following gases at the following flow rates: helium (250 l/min), nitrogen (285 l/min), monosilane (2.5 l/min), ethylene (15 l/min) and oxygen (10 l/min). For Example 42, the same gases and flow rates were used except for monosilane (2.3 l/min), ethylene (13.8 l/min) and oxygen (9.2 l/min). Where two coaters were used to deposit the silicon oxide layer in Examples 30 to 42, the above flow rates were used for each coater.

[0075] In Examples 30-42 the deposition temperatures (i.e. the temperature of the float glass ribbon under the coater corresponding to each of the coaters 27-30) was as indicated in Table 7. The temperatures in Table 7 have an uncertainty of about $\pm 50^\circ\text{F}$ ($\pm 28^\circ\text{C}$). The extraction for each coater was at approximately 2 mbar.

TABLE 7

Coater	Approx. Temperature of Glass Ribbon
27	1330°F (721°C)
28	1275°F (690°C)
29	1250°F (677°C)
30	1150°F (621°C)

[0076] Titanium tetrachloride (TiCl_4) and ethyl acetate were entrained in separate nitrogen/helium carrier gas streams. For the evaporation of TiCl_4 a thin film evaporator was used. The liquid TiCl_4 was held in a pressurised container (head pressure approx 5 psi). This was used to deliver the liquid to a metering pump and Coriolis-force flow measurement system. The metered flow of the precursor was then fed into a thin film evaporator at a temperature of 110°F (43°C). The TiCl_4 was then entrained in the carrier gas (helium) and delivered to the mixing point down lines held at 250°F (121°C). The ethyl acetate was delivered in a similar way. The liquid ethyl acetate was held in a pressurised container (head pressure approx 5 psi). This was used to deliver the liquid to a metering pump and Coriolis force flow measurement system. The metered flow of the precursor was then fed into a thin film evaporator at a temperature of 268°F (131°C). The evaporated ethyl acetate was then entrained in the carrier gas (helium/nitrogen mixture) and delivered to the mixing point down lines held at approximately 250°F (121°C).

[0077] The TiCl_4 and ethyl acetate gas streams were combined to form the gaseous mixture used to deposit the titanium oxide layer. This mixing point was just prior to the coater.

[0078] The line speed of the float glass ribbon, the temperature of deposition of the silicon oxide and temperature of deposition of the titanium oxide layers and the flow rates of the He/N_2 bulk carrier gas and the flow rate of TiCl_4 and ethyl acetate are described for Examples 30-42 in Table 8.

[0079] The coated float glass ribbon was cooled and cut and the optical properties and photocatalytic activity of samples determined. Table 9 describes the haze, optical properties in transmission and reflection (visible percent transmission/reflection and colour co-ordinates using the LAB system) of the samples. The coated glasses were subjected to abrasion testing in accordance with BS EN 1096, in which a sample of size 300mm x 300mm is fixed rigidly, at the four corners, to the test bed ensuring that no movement of the sample is possible. An unused felt pad cut to the dimensions stated in the standard (BS EN 1096 Part 2 (1999)) is then mounted in the test finger and the finger lowered to the glass surface. A load pressure on the test finger of 4N is then set and the test started. The finger is allowed to reciprocate across the sample for 500 strokes at a speed of 60 strokes/min \pm 6 strokes/min. Upon completion of this abrasion the sample is removed and inspected optically and in terms of photocatalytic activity. The sample is deemed to have passed the test if the abrasion results in a change in transmission of no more than $\pm 5\%$ when measured at 550nm and the coated substrate remains photocatalytically active which means that, after the test irradiation by UV light for 2 hours reduces the static water contact angle to below 15°.

[0080] The glasses were also subjected to a humidity cycling test in which the coating is subjected to a temperature cycle of 35°C to 75°C to 35°C in 4 hours at near 100% relative humidity.

[0081] The static water contact angle of the coated glasses as produced and after 130 minutes of UV irradiation (UVA 351 mm lamp at approximately 32 W/m²) and after 300, 500 and/or 1000 strokes of the European standard abrasion test described in Table 10. The contact angle of the abraded samples was determined after irradiation for 2 hours.

[0082] The samples deposited at the higher temperatures of 1330-1250°F (721°C to 677°C) were photocatalytically active even after 1000 European standard abrasion strokes or after 200 humidity cycles. The photocatalytic activity in terms of $t_{90\%}$ of the coated glasses as produced and after 300, 500 and/or 1000 strokes of the European standard abrasion test and after 200 humidity testing cycles are described in Table 11. In Table 11, the term Active indicates that the coated glasses were photocatalytically active but that $t_{90\%}$ was not determined.

TABLE 8

Example	Line-Speed (m/min)	Silica layer Deposition Temperature /°C	Titanium Oxide Layer			
			Deposition Temperature /°C	Flow Rates of Carrier Gases		Flow Rates of Precursors
				He L/min	N ₂ L/min	TiCl ₄ cc/min Ethyl Acetate cc/min
30	10.9	690 & 677	621	300	300	6.3 16.3
31	10.9	690 & 677	621	300	300	6.3 16.3
32	10.9	690 & 677	621	300	300	6.3 16.3
33	10.9	690 & 677	621	300	300	6.3 16.3
34	10.9	690	621	300	300	6 16
35	10.9	690	621	300	300	6 16
36	10.9	690	621	300	300	6 16
37	10.9	690	677	300	300	5.5 14.7
38	10.9	690	677	300	300	5.5 14.7
39	10.9	690	677	300	300	5.5 14.7
40	10.9	690	677	300	300	5.5 14.7
41	6.5	721	690	300	300	4 10.7
42	12.1	721 & 690	677	300	300	9.5 25.4

TABLE 9

Example	Film Side Reflection				Transmission				Haze (%)
	R (%)	L*	a	b	T (%)	L*	a	b	
30	14.2	44.5	0.3	-10.3	84.3	93.6	-1.2	3.6	0.11
31	14.6	45.1	0.3	-10.4	84.5	93.7	-1.1	3.4	0.30
32	14.6	45.1	0.3	-10.5	84.3	93.6	-1.1	3.6	0.12
33	13.8	44.0	0.3	-9.8	85.5	94.1	-1.1	2.9	0.15
34	13.6	43.7	0.1	-8.7	84.8	93.8	-1.1	2.7	0.12
35	13.8	43.9	0.1	-8.8	85.4	94.1	-1.1	2.6	0.11
36	12.9	42.6	0.1	-8.2	85.8	94.2	-1.1	2.5	0.14
37	12.6	42.2	0.1	-7.9	86.1	94.4	-1.1	2.3	0.08
38	11.9	41.0	0.1	-6.9	87.1	94.8	-1.1	1.7	0.07
39	11.5	40.4	0.0	-6.5	87.2	94.8	-1.1	1.8	0.10
40	11.6	40.6	0.0	-6.6	86.9	94.7	-1.1	1.8	0.08
41	a	a	a	a	a	a	a	a	a
42	14	44.3	0.1	-9.9	84.8	93.8	-1.1	3.1	0.14

a Not Measured

TABLE 10

Example	Static Water Contact Angle (°) after Number of Abrasion Strokes				
	0	0 (after Irradiation 130 min UV)	300	500	1000
30	2.3	3.3	failed		
31	2.0	3.2	failed		
32	a	a	failed		
33	2.0	3.2	failed		
34	a	a	failed		
35	2.0	3.2	failed		
36	2.1	3.4	failed		
37	2.2	3.3		<15	
38	2.0	3.1		<15	
39	1.9	3.1		<15	
40	2.2	3.2		<15	
41	7.8	7.8			10.1
42	4.7 - 5.3	4.7 - 5.3			5.6 - 9.8

a Not measured

TABLE 11

Example	t _{90%} (min) after Number of Abrasion Strokes				t _{90%} (min) after 200 Humidity Cycles
	0	300	500	1000	
30	7.5	failed			failed
31	18.5	failed			failed
32	8.5	failed			failed
33	8	failed			failed
34	21	failed			failed
35	4	failed			failed
36	8.5	failed			failed
37	15.5		Ca. 2160		Active
38	18.5		Ca. 2160		Active
39	17		Ca. 2160		Active
40	18.5		Ca. 2160		Active
41	a			ca. 2160	Active
42	45			2800	Active

a Not measured

Claims

1. A photocatalytically active coated substrate comprising a substrate having a photocatalytically active titanium oxide coating on one surface thereof, characterised in that the coated surface of the substrate has a photocatalytic

activity of greater than $5 \times 10^{-3} \text{ cm}^{-1} \text{ min}^{-1}$ and in that the coated substrate has a visible light reflection measured on the coated side of 35% or lower.

- 5 2. A photocatalytically active coated substrate as claimed in claim 1 wherein the coated surface of the substrate has a photocatalytic activity of greater than $1 \times 10^{-2} \text{ cm}^{-1} \text{ min}^{-1}$.
3. A photocatalytically active coated substrate as claimed in claim 2 wherein the coated surface of the substrate has a photocatalytic activity of greater than $3 \times 10^{-2} \text{ cm}^{-1} \text{ min}^{-1}$.
- 10 4. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the coated substrate has a visible light reflection measured on the coated side of 20% or lower.
5. A photocatalytically active coated substrate as claimed in claim 4 wherein the coated substrate has a visible light reflection measured on the coated side of 15% or lower.
- 15 6. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the substrate comprises a glass substrate.
- 20 7. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the coated substrate has an alkali metal ion blocking under layer between the surface of the substrate and the photocatalytically active titanium oxide coating.
8. A photocatalytically active coated substrate as claimed in claim 7 wherein the alkali metal ion blocking layer is a layer of silicon oxide.
- 25 9. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the photocatalytically active titanium oxide coating has a thickness of 30 nm or lower.
- 30 10. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the photocatalytically active titanium oxide coating has a thickness of 20 nm or lower.
11. A photocatalytically active coated substrate as claimed in claim 10 wherein the photocatalytically active titanium oxide coating has a thickness in the range 2 nm to 20 nm.
- 35 12. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the coated surface of the substrate has a static water contact angle of 20° or lower.
13. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the coated substrate has a haze of less than 1%.
- 40 14. A photocatalytically active coated substrate as claimed in any of the preceding claims wherein the coated surface of the substrate is durable to abrasion, such that the coated surface remains photocatalytically active after it has been subjected to 300 strokes of the European standard abrasion test.
- 45 15. A photocatalytically active coated substrate as claimed in claim 14 wherein the coated surface remains photocatalytically active after it has been subjected to 500 strokes of the European standard abrasion test.
16. A photocatalytically active coated substrate as claimed in claim 15 wherein the coated surface remains photocatalytically active after it has been subjected to 1000 strokes of the European standard abrasion test.
- 50 17. A photocatalytically active coated substrate as claimed any of claims 14 to 16 wherein the haze of the coated substrate is 2% or lower after being subjected to the European abrasion test.
- 55 18. A photocatalytically active coated substrate as claimed in any of preceding claims wherein the coated surface of the substrate is durable to humidity cycling such that the coated surface remains photocatalytically active after the coated substrate has been subjected to 200 cycles of the humidity cycling test.
19. A durable photocatalytically active coated glass comprising a glass substrate having a coating on one surfac

thereof, said coating comprising an alkali metal ion blocking underlayer and an outer photocatalytically active titanium oxide layer, wherein the coated surface of the substrate is durable to abrasion such that the coated surface remains photocatalytically active after it has been subjected to 300 strokes of the European standard abrasion test.

- 5 **20.** A durable photocatalytically active coated glass as claimed in claim 19 wherein the coated glass has a visible light reflection measured on the coated side of 35% or lower, and wherein the photocatalytically active titanium oxide layer has a thickness of 30 nm or lower.
- 10 **21.** A coated glass comprising a glass substrate having a photocatalytically active titanium oxide coating on one surface thereof, **characterised in that** the coated surface of the glass has a photocatalytic activity of greater than $8 \times 10^{-2} \text{cm}^{-1} \text{min}^{-1}$ and **in that** the coated glass has a visible light reflection measured on the coated side of less than 20%.
- 15 **22.** A multiple glazing unit comprising a first glazing pane of a coated substrate as claimed in any of the preceding claims in spaced, opposed relationship to a second glazing pane.
- 20 **23.** Laminated glass comprising a first glass ply of a coated glass as claimed in any of claims 1 to 21, a polymer interlayer, and a second glass ply.

20

25

30

35

40

45

50

55

Fig.1.





Fig.2.





(11) **EP 1 254 870 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
02.01.2003 Bulletin 2003/01

(51) Int Cl.7: **C03C 17/245, C03C 17/34,
C23C 16/40**

(43) Date of publication A2:
06.11.2002 Bulletin 2002/45

(21) Application number: **02009640.0**

(22) Date of filing: **01.06.2000**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **08.06.1999 GB 9913315**

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
00935378.0 / 1 198 431

(71) Applicants:

- **PILKINGTON PLC**
St. Helens, Merseyside WA10 3TT (GB)
- **Pilkington North America, Inc.,**
as Libbey-Owens-Ford Co
Toledo, Ohio 43695 (US)

(72) Inventors:


- **Ammerlaan, Johannes Andreas Maria**
5615 CJ Eindhoven (NL)
- **McCurdy, Richard Joseph**
Aurora, IL 60506 (US)
- **Hurst, Simon James**
Cheshire WA7 1QW (GB)

(74) Representative: **Halliwell, Anthony Charles et al**
Group Intellectual Property Dept,
Pilkington European Technical Centre,
Pilkington plc,
Hall Lane,
Lathom
Ormskirk, Lancashire L40 5UF (GB)

(54) **Photocatalytically active coated substrates**

(57) A self cleaning photocatalytically active coated substrate, especially a glass substrate, is disclosed, the coated substrate having a photocatalytically active titanium oxide coating on one surface thereof. The coated substrate exhibits, in one aspect, high photocatalytic ac-

tivity of greater than $5 \times 10^{-3} \text{ cm}^{-1} \text{ min}^{-1}$ and low visible light reflection measured on the coated side of 35% or lower and in another aspect is durable to abrasion such that the coated surface remains photocatalytically active after it has been subjected to 300 strokes of the European standard abrasion test.



EP 1 254 870 A3



European Patent
Office

PARTIAL EUROPEAN SEARCH REPORT

Application Number

which under Rule 45 of the European Patent Convention shall be considered, for the purposes of subsequent proceedings, as the European search report

EP 02 00 9640

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D,X, Y	WO 98 06675 A (HURST SIMON JAMES ;SHEEL DAVID WILLIAM (GB); PILKINGTON PLC (GB);) 19 February 1998 (1998-02-19) * page 6, line 4, paragraph 4 - page 9, line 9; examples 1-7 * * page 25, last paragraph - page 27, paragraph 3 *	1-23	C03C17/245 C03C17/34 C23C16/40
D,X, Y	WO 98 41480 A (PPG INDUSTRIES INC) 24 September 1998 (1998-09-24) * page 4, line 2 - line 21 * * page 6, line 3 - page 7, line 16 * * page 9, line 24 - page 10, line 19 * * page 16, line 29 - page 19, line 15 *	1-23	
D,A	EP 0 901 991 A (CENTRAL GLASS CO LTD) 17 March 1999 (1999-03-17) * paragraph '0005! - paragraph '0008! * * paragraph '0010! - paragraph '0013! *	1-23	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C03C C23C
INCOMPLETE SEARCH			
<p>The Search Division considers that the present application, or one or more of its claims, does/does not comply with the EPC to such an extent that a meaningful search into the state of the art cannot be carried out, or can only be carried out partially, for those claims.</p> <p>Claims searched completely :</p> <p>Claims searched incompletely :</p> <p>Claims not searched :</p> <p>Reason for the limitation of the search:</p> <p>see sheet C</p>			
Place of search		Date of completion of the search	Examiner
THE HAGUE		15 October 2002	Van Bommel, L
CATEGORY OF CITED DOCUMENTS		<p>T: theory or principle underlying the invention</p> <p>E: earlier patent document, but published on, or after the filing date</p> <p>D: document cited in the application</p> <p>L: document cited for other reasons</p> <p>A: member of the same patent family, corresponding document</p>	
<p>X: particularly relevant if taken alone</p> <p>Y: particularly relevant if combined with another document of the same category</p> <p>A: technological background</p> <p>O: non-written disclosure</p> <p>P: intermediate document</p>			

EP 1 254 870 A3 (04/02/01)



Europäisches
Patentamt

UNVOLLSTÄNDIGE RECHERCHE
ERGÄNZUNGSBLATT C

Nummer der Anmeldung
EP 02 00 9640

Claim(s) searched incompletely:
1-23

Reason for the limitation of the search:

Present claims 1 - 23 relate to a products defined (inter alia) by reference to the following parameter(s): photocatalytic activity, visible light reflection, haze, humidity durability and abrasion durability. The use of these parameters in the present context is considered to lead to a lack of clarity within the meaning of Article 84 EPC. It is impossible to compare the parameters the applicant has chosen to employ with what is set out in the prior art. The lack of clarity is such as to render a meaningful complete search impossible. Consequently, the search has been restricted to documents disclosing processes that would result in such products by virtue of process steps as disclosed in the description, page 2, second paragraph to page 4, second paragraph.

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 00 9640

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-10-2002

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9806675	A	19-02-1998	AU 718133 B2	06-04-2000
			AU 3948397 A	06-03-1998
			BR 9711058 A	17-08-1999
			CA 2262504 A1	19-02-1998
			CN 1228067 A	08-09-1999
			CZ 9900402 A3	11-08-1999
			EP 1238948 A1	11-09-2002
			EP 0944557 A1	29-09-1999
			WO 9806675 A1	19-02-1998
			JP 2001503005 T	06-03-2001
			TW 410214 B	01-11-2000
			ZA 9707211 A	12-02-1998
WO 9841480	A	24-09-1998	US 6027766 A	22-02-2000
			AU 737164 B2	09-08-2001
			AU 6698698 A	12-10-1998
			BR 9808337 A	16-05-2000
			CN 1260767 T	19-07-2000
			EP 0966409 A1	29-12-1999
			JP 2000513695 T	17-10-2000
			PL 335736 A1	08-05-2000
			SK 119299 A3	11-12-2000
			TR 9902245 T2	21-11-2000
			US 2002114945 A1	22-08-2002
			WO 9841480 A1	24-09-1998
			US 6413581 B1	02-07-2002
			US 6054227 A	25-04-2000
			HU 0001814 A2	28-09-2000
EP 0901991	A	17-03-1999	JP 11079788 A	23-03-1999
			EP 0901991 A2	17-03-1999

EPO FORM P0463

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82